
Technical data StyleBoard MDF top

Thickness (nominal)	> 12 mm to ≤ 19 mm
Tolerance on thickness (EN 324-1)	± 0.2 mm
Tolerance on length and width (EN 324-1)	± 5 mm
Edge straightness tolerance (EN 324-2)	1.5 mm per m
Squareness tolerance (EN 324-2)	2 mm per m
Moisture content past production (EN 322)	6 % ± 2 %
Class of emission, formaldehyde	E1
Internal bond (EN 319)	0.60 N/mm ²
Bending strength (EN 310)	27 N/mm ²
Modulus of elasticity in bending (EN 310)	2400 N/mm ²
Mean density (EN 323)	740 kg/m ³

All values correspond as approximate values to our production values and guidelines. The mentioned values are for information only and don't represent assured characteristic values. Tolerance on the mean density within and between the boards according to table 1, European Standard 622-1. Subject to change without notice.

All prior issues of this technical data sheet for the mentioned type of board above are invalid with this release.